

High Performance Vapour Barrier

CE Mark to EN 13984

Page 1



nbsPlus

- Range suitable for all internal building conditions
- Used within roof, wall and floor constructions
- Reduces the likelihood of interstitial condensation
- Vapour resistance of 1100 MNs/g

Description

Visqueen High Performance Vapour Barrier is used to omit the risk of interstitial condensation within a structure as well as improving the general airtightness of the building. Visqueen High Performance Vapour Barrier restricts the passage of warm, moist air from within the building from permeating into the structure or the roof. It is commonly used within timber frame housing as well as commercial buildings.

Visqueen High Performance Vapour Barrier is a tough multi layer reinforced HDPE membrane with an aluminium foil.

Application

The control of condensation to within safe limits is an important consideration in the design and construction of buildings. The occupants of a building and their associated activities produce water vapour which, if unmanaged, can condense within or between building elements; a process referred to as interstitial condensation. This condensation can have serious detrimental effects upon the fabric of the building such as causing the decay of timber elements and corrosion of metal components, and reducing the thermal effectiveness of insulating materials.

With the progressive increases in thermal efficiencies of buildings in order to reduce energy usage, any reduction in the effectiveness of the installed insulation can have long term financial implications. The negative effect upon the fabric of the building increases the incidence of moulds and mildews, which in turn can have a harmful effect upon the health of the building occupants.

Visqueen HP Vapour Barrier provides a means of protecting the warm side of the thermal insulation incorporated in a building by creating a barrier to the movement of warm, moist air.

Visqueen HP Vapour Barrier is a loose laid membrane designed for use in roofs, walls and floors subjected to humidity levels more than 60% at 20 degrees Celsius (BS5250: 2002 class 4 and 5 conditions) e.g. domestic dwellings with high occupancy, sports halls, swimming pools, communal shower areas, laundries, canteens and buildings with wet industrial processes.

Installation Fixing

Visqueen Vapour Control Layers should be installed in accordance with the recommendations of BS5250: 2002 'Code of practice for control of condensation in buildings'. Visqueen HP Vapour Barrier should be installed on the "warm" side of the insulated structure, with special care being taken to ensure that all seams and holes are sealed effectively - thus rendering the whole structure moisture and vapour proof and improving thermal performance. It is important that Visqueen HP Vapour barrier should be continuous in order to prevent vapour entering the wall or the roof.

VISQUEEN
 BUILDING PRODUCTS



High Performance Vapour Barrier

CE Mark to EN 13984

Page 2

The High Performance Vapour Barrier membrane should be installed with the foil (silver) side facing the warm inside of the building.

Jointing Tapes Ensure all surfaces are clean, smooth and dry prior to the application of Visqueen Vapour Tape or Visqueen Vapour Edge Tape. Surfaces do not require priming prior to tape application. For total protection, all joints in the HP vapour barrier should be lapped by a minimum of 75mm, and sealed with Visqueen Vapour Tape applied equidistant over the lap. To aid formation, laps should be made over a solid substrate. For protecting and sealing the perimeter, Visqueen Vapour Edge Tape should be used. Where perimeter detailing involves sealing to masonry units such as brickwork, blockwork, etc ensure vapour proof continuity by sealing with Visqueen Vapour Edge Tape applied equidistant over the junction. Visqueen Vapour tapes are coated with a special cold weather acrylic pressure sensitive adhesive system which combines superior quick stick at normal temperatures with superior low temperature performance below freezing. The tapes are highly puncture and tear resistant. Failure to suitably connect the vapour control layer to other building elements will seriously reduce performance.

Additional System Components Visqueen Preformed Top Hat unit –preformed unit for sealing around service pipe penetrations.

Precautions Visqueen Vapour Control Layers are classified as non-hazardous when used in accordance with BS5250: 2002. Care should be taken to avoid accidental damage when handling the membranes on site. Membrane installation is not recommended below 5oC. Visqueen Vapour Control Layers are not intended for use where they will be exposed for long periods of outdoor weathering. When the Vapour Barrier is to be installed near a light fitting please consult with Building Control or the Architect on the suitability of the product. Material softening point is declared in our technical data.

Technical Data and CE Mark

Visqueen Vapour Check complies with the requirements and clauses of EN 13984 - Flexible sheets for waterproofing - Plastic and rubber vapour control layers - Definitions and characteristics.



High Performance Vapour Barrier

CE Mark to EN 13984

Product Data

Product Data

heading	Characteristic	Test method	Units	Compliance criteria	Value or Statement
	Visible defects	EN 1850 -2	-	Pass/Fail	Pass
	Length	EN 1848-2	m	-0%/+10%	25 or 50
	Width	EN 1848-2	m	-2.5%/+2.5%	2
	Thickness	EN 1849-2	mm	-12.5%/+12.5%	0.52
	Mass	EN 1849-2	g/m2	-12.5%/+12.5%	345
	Tensile Strength - MD	EN EN12311	N	>MLV	515
	Tensile Strength - CD	EN EN12311	N	>MLV	550
	Tensile Elongation - MD	EN EN12311	%	>MLV	17
	Tensile Elongation - CD	EN EN12311	%	>MLV	15
	Joint Strength	EN12317-2	N	>MLV	332
	Watertightness 2kPa	EN 1928	-	Pass/Fail	Pass
	Resistance to impact	EN 12691	mm	>MLV	200
	Low temperature flexibility	EN 495-5	oC	-40	Pass
	Durability (artificial ageing)	EN 1296 and EN 1928	-	Pass/Fail	Pass
	Durability Chemical Resistance	EN 1847	-	Pass/Fail	Pass
	Resistance to tearing (nail shank) CD	EN 12310-1	N	MDV	358
	Resistance to tearing (nail shank) MD	EN 12310-1	N	MDV	368
	Resistance to static loading	EN 12730	Kg	>MLV	Pass 20
	Water vapour transmission - resistance	EN 1931	MNs/g	MDV	
	Water vapour transmission - permeability	EN 1931	g/m2/d	MDV	0.03
	Reaction to Fire	EN 13501-1	Class	MDV	F



High Performance Vapour Barrier

CE Mark to EN 13984

Appendix A



nssPlus

Visqueen Building Products

Visqueen is the market leader in the manufacture and supply of structural waterproofing and gas protection systems. Visqueen offers the complete package - a proven, reliable range backed by a technical support service that goes unmatched in the market - everything you would expect from a reputable and ethical company.

System Accessories

To ensure full waterproofing protection please use the following certified system components:

- Visqueen High Performance (HP) Tanking Primer
- Visqueen TreadGUARD1500
- Visqueen Protect&Drain
- Visqueen Top Hat Unit

Downloads Library

- Technical Datasheet
- Declaration of Performance
- Visqueen's Guide to CE Marking

Find your local stockist

Search our directory of Visqueen specification Stocking Centres to locate your nearest Visqueen Partner.

Distributor Support

Our specification Stocking Centres can access a free library of sales support tools, bespoke catalogues and more, [click here](#).

Technical support throughout your project

We are specialists in our field and can help you specify the correct solutions with the necessary performance levels, in accordance with building regulations.

- Nationwide site support team
- Specification advice
- Installation guidance & project sign off
- System design including CAD details

